

PRODUCT DATA

Date: June 2009



Code: 00679/30

IDENDEN PVA SEALER 30-17

Idenden PVA Sealer 30-17 is a PVA emulsion designed as a primer or as a sealer for a variety of applications. For example, coating and sealing residual fibres left after stripping asbestos insulation, sealing very porous asbestos prior to encapsulating with Idenden Sprayable Vapour Barrier Coating ET-150; as a fibre suppressant on polythene sheeting prior to de-tenting after asbestos removal or as a dust sealer for brick walls and for calcium silicate boards and foams. Idenden PVA Sealer 30-17 can be applied by brush, roller or spray and provides a tough clear protective coating.

Solvent for cleaning up

Directions for use

carrying out the work.

IMPORTANT

Wet: Water Dry: Hot soapy water

Before embarking on any work involving Idenden PVA Sealer 30-17 the separate Safety Data Sheet should be carefully studied by those

 All surfaces must be clean, dry and free from dust and any loose materials. In the case of asbestos, dust and loose particles should be vacuumed up. Use within the constraints of current

Idenden PVA Sealer 30-17 may be applied neat or diluted with 5-10% clean cold water, and then applied to the asbestos insulation by airless spray. Leave to dry overnight before encapsulating with Idenden Sprayable Vapour Barrier Coating ET-150 in accordance with the separate data sheets.

For applications by brush, roller or airless spray, dilute with up to

After removal of asbestos, Idenden PVA Sealer 30-17 should be sprayed onto the inside of the polythene confinement tenting to "fix" fibres prior to de-tenting. Dilute with four parts of clean cold water to one part of Idenden PVA Sealer 30-17. No dividing or

legislation or only on HSE guidance.
A) ASBESTOS COATING AND SEALING

B) BUILDING DUST SEALER

C) ASBESTOS FIBRE SUPPRESSANT

separation should occur between polythene.

50% clean cold water.

Features

- Asbestos fibre stabiliser
- · Easily applied by brush, roller or spray
- Water based
- Dries transparent
- Semi-flexible
- Wide service temperature range

Product Characteristics

Colour	White (dries clear)		
Form	Liquid		
Weight per litre	1.07 kg 35% solids		
Composition	Synthetic resin emulsion		
Packaging	5 litre polyjerry		
Shelf life/storage	At least 12 months from date of manufacture when stored unopened in a cool, dry place within the temperature range +5°C to +25°C and out of direct sunlight. PROTECT FROM FROST		

Typical Performance Data (approx.)

Drying time	30 minutes to 4 hours, dependant on ambient conditions and absorption	3.	Do not apply Idenden PVA Sealer 30-17 externally in wet weather or if rain or snow is imminent. Do not use below +5°C.	
	by substrate		SPRAY INSTRUCTIONS	
Service temperature	-10°C to +80°C		Idenden PVA Sealer 30-17 may be sprayed with a variety of airless spray systems. However, the following system has produced the best results under test:	
Application temperature	Above +5°C			
Reaction to fire	Wet: Non-flammable Dry: Burns slowly		Pump: Fluid Hose: Gun:	Airlessco 5100/Graco Ultra 1095 Up to 15 m, 7 mm diameter Over 15 m, 9 mm diameter Silver type or equivalent
Coverage Asbestos fibre suppressant – 15-20 square metres per litre Asbestos coating and sealing – 3-5 square metres per litre Building dust sealer – 6-8 square metres per litre		Tip:	0.015-0.023 Reverse-a-quick nozzle	
	Asbestos coating and sealing –		During spraying wear suitable respiratory equipment.	
	Building dust sealer –	5.	Clean application equipment and remove excess uncured sealer with cold water and cured sealer with hot soapy water.	

See final page for disclaimer.

Bostik Limited, Common Road, Stafford, ST16 3EH, England

Tel: +44 (0)1785 272727

Fax: +44 (0)1785 257898

www.bostik.co.uk

NOTE: Removal or encapsulation of asbestos containing material, dismantling of any confinement structure and disposal of both asbestos and contaminated materials should be done strictly within current regulations and codes of practice and only by an approved contractor.

Precautions in Use

For health and safety instruction, first aid measures and spillage and disposal instructions, see separate health and safety data sheet for Idenden PVA Sealer 30-17.

Disclaimer - please read carefully

This disclaimer is issued by Bostik Limited ("the Company") and applies to the use of any products supplied by the Company ("the Products") displayed on this Technical Data Sheet ("TDS"). Please read this disclaimer carefully before using any of the Products. Using this TDS and/or the Product constitutes your acceptance of this disclaimer. Its contents shall prevail over any directions of use and any disclaimer and/or exclusion or limitation of liability of the Company which may appear on the packaging of the Products.

This disclaimer sets out the entire financial liability of the Company (including any liability for the acts or omissions of its employees, agents and sub-contractors) to any user of the Products ("Product User") in respect of any use made or resale by the Product User, of any of the Products in this TDS.

This disclaimer does not affect the Company's liability for death or personal injury arising from the Company's negligence in respect of the Products, nor its liability for fraud, or fraudulent misrepresentation, nor any other liability which cannot be excluded or limited under applicable law.

The Company's total liability however arising and whether caused by tort (including negligence and breach of statutory duty), breach of contract or otherwise, arising in connection with the use made or resale by the Product User of any of the Products in this TDS shall be limited to the price paid for the Product by the Product User.

The Company shall not be liable to the Product User for any pure economic loss, loss of profit, loss of business, depletion of goodwill or otherwise, in each case whether direct, indirect or consequential, or any claims (including in respect of personal injury insofar as not caused by the Company's negligence) for consequential compensation whatsoever (howsoever caused) which arise out of or in connection with the use made or resale by the Product User of any of the Products in this TDS.

The Company shall not be liable to the Product User in relation to any loss for any use which is inappropriate or use which is otherwise than in accordance with the relevant instructions for use of the Products in this TDS or on the Product. Product Users are advised to confirm the suitability of the Products by their own tests.

This TDS covers just one of a large range of products supplied by the Company. Full information on these products and advice on application is freely available from our fully trained staff throughout the country. In addition, specialist technical advice is available from our Technical Services Department. This TDS supersedes all previous TDSs relating to the Products, and users of it must ensure that it is the current issue. Destroy all previous TDSs, and if in any doubt, contact the Company, quoting the code number in the torigith advice on the front of this document. Bostik Limited, Common Road, Stafford, ST16 3EH, England Tel: +44 (0)1785 272727 Fax: +44 (0)1785 257898 www.bostik.co.uk

BOSTIK, EVO-STIK, CEMENTONE, VALLANCE, IDENDEN, LAYBOND & SEALOCRETE ARE REGISTERED TRADEMARKS OF BOSTIK LIMITED.